

## Natural Prestige Laminate Floors

### Technical Information and Specifications

<b>Test</b>	<b>Measure</b>	<b>Test Method</b>
Wear Resistance	AC4	EN 13329: 2000
Level of Use	Approved for Commercial Classes 31	EN 13329: 2000
Impact Resistance	IC1	EN 13329: 2000
Static Resistance (mm)	No Visible Change $\leq$ 0.01 mm Indentation	EN 13329: 2000
Resistance to cigarette burns	Class 4 Exceeds Requirements (Best Value)	EN 13329: 2000
Resistance to staining	Class 5 Exceeds Requirements (Best Value)	EN 13329: 2000
Light Resistance	No Effect/Class 6 (Blue Wool) Class 4 (Gray Scale)	EN 13329: 2000
Thermal insulation including PE film and foam	<0.10m <sup>2</sup> K/W	DIN 52612
Anti-Static resistance	2x10 <sup>10</sup> ohm	DIN 51953
Electric charge deviation	0.9kV	DIN 54345
Caster Chair	25,000 Cycles No Damage	EN 13329: 2000
Formaldehyde Emission	<0.10ppm	EN 717 ASTM 1333
Slip resistance	0.60 SCOF	ASTM C1028-89
Smoke Density – Flaming	226	ASTM E 662-95
Smoke Density – Non flaming	324	ASTM E 662-95
Critical Radiant Flux	Class 1 Exceeds Requirements (Best Value)	ASTM E 648-91

### Product Specifications

Total Plank Thickness	10mm
Joint	Glueless Click
Core material	Premium high density fibreboard
Plank Dimensions	50.63" x 6.30" (1,286mm x 160mm)
	8 planks per carton (17.72 sq. ft.)
Warranty	Lifetime Limited Residential 10 Years Limited Commercial